



## KLINGERSil C-4106

### Typical Specifications

<i>Compressibility ASTM F 36 A</i>		30%
<i>Recovery ASTM F 36 A</i>		50%
<i>Stress relaxation DIN 52913</i>	<i>50MPa, 16h/300<sup>0</sup>C</i>	15MPa
<i>Gas leakage according to DIN 3535/6</i>		<0.1ml/min
<i>Chlorides (soluble)</i>		150ppm
<i>Thickness increase after fluid</i>	<i>Oil nr.3:5h/150<sup>0</sup>C</i>	5%
<i>Immersion ASTM F 146</i>	<i>Fuel B:5h/23<sup>0</sup>C</i>	7%
<i>Density</i>		1.0g/cm <sup>3</sup>